

# CemBase Asphalt Fortifier

## Commercial Product Data Sheet



### RECOMMENDED USES

- StreetBond® CemBase Asphalt Fortifier fortifies asphalt pavement to help resist scuffing on weaker stamped asphalt such as driveways or pathways.
- Applied as the two initial layers in a StreetBond application over a printed surface that needs fortification.
- StreetBond CemBase Asphalt Fortifier is combined with StreetBond Colorants to offer a wide range of colors and can also be combined with StreetBond Solar Reflective (SR) Colorants to produce a cool pavement surfaces for compliance with LEED specifications for urban heat island mitigation and to provide more comfortable environments.
- StreetBond CemBase Asphalt Fortifier is applied in two layers as a base coat and must always be covered with at least one layer StreetBond SB150. For example, if a project would typical require four layers of StreetBond SB150 on a stamped asphalt surface, a project needing fortification would have two layers of StreetBond CemBase Asphalt Fortifier applied, followed by two layers of StreetBond SB150.

### PRODUCT DESCRIPTION

StreetBond CemBase Asphalt Fortifier is a high-performance cementitious, epoxy-modified acrylic based, waterborne surfacing product designed for application on stamped (textured) asphalt pavements only. StreetBond CemBase Asphalt Fortifier fortifies asphalt pavement to help resist scuffing on weaker stamped asphalt such as driveways or pathways. StreetBond CemBase Asphalt Fortifier is worker safe, environmentally safe, creates no unpleasant odors (during or after installation) and meets EPA requirements for Volatile Organic Compounds (VOC). StreetBond SB150's friction properties are suitable for both pedestrian and vehicular applications.

### WARRANTY

See applicable warranties for complete coverage and restrictions.

### PACKAGING & SHELF LIFE

One unit (box) of StreetBond CemBase Asphalt Fortifier consists of:

- One 1.6 gallon (6.0 liter) jug of StreetBond CemBase Asphalt Fortifier Resin
- One Bag of Dry hardener and silica aggregate. One Chosen StreetBond Colorant (sold separately)

Shelf life is 24 months if unopened containers stored between 40°F and 90°F (4°C and 32°C).

### PRODUCT CHARACTERISTICS

CEMBASE ASPHALT FORTIFIER	
Volume Solids	60% ±2% [ASTM D2697]
Weight Solids	74% ±2% [ASTM D2369]
VOC (calculated)	<25 g/L
Freeze Point	32°F (0°C)
Density	14.2 lb/gal (1.70 g/mL)
Mandrel Bend	3/8" @ 21°C
Water Absorption	10.2%
Permeance	13.43 g/m² / 24 hr/mmHg (52 mils)


Application Temperature	50°F to 105°F (10°C to 40°C)
Drying Time (Touch Dry)	1-4 hours at 77°F (25°C) and 40% humidity [ASTM D5895]
Taber Abrasion (Dry)	0.41 g/100 cycles
Taber Abrasion (Wet)	6.92 g/100 cycles

### APPLICATION INSTRUCTIONS

**Mixing Instructions:** Shake resin jug to mix components and pour contents into a clean 5 gallon pail. Add colorant and ½ a jug of water (1/3 jug for cool days and 2/3 jug for hot days). Mix liquid for 30 seconds to evenly distribute the colorant. While continuing to mix, slowly add the bag of dry hardener and continue mixing for 3 minutes once the bag is empty. Product must be used immediately.

**Surface Preparation:** Dirt, debris, water and contaminants sitting on the surface will affect adhesion. Thoroughly clean surface using a broom and backpack blower or, in severe situations, use a power washer.

Areas containing chemical contaminants such as vehicle fluids need to be treated using a degreasing solution. Proper removal of contaminants and degreasing solution is necessary prior to coating application. Care should be taken to ensure that the substrate is dry before applying the coating. Consult the StreetBond Substrate Guide if unsure of the quality of the surface. An environmentally-friendly cleaner should be used. StreetBond Adhesion Promoter may be used for polished asphalt. No precipitation should be expected within 24 hours of product application.



continued on next page

# CemBase Asphalt Fortifier

## Commercial Product Data Sheet

### APPLICATION INSTRUCTIONS, CONT'D

**Recommended Application:** StreetBond CemBase Asphalt Fortifier may be applied in thin coats by brush, roller or textured sprayer. It should always be applied in two layers as a base coat. Base coat must always be covered with at least one layer StreetBond SB150.

Consult the most up-to-date StreetBond Stamped Surface Specification at [streetbond.com](http://streetbond.com) for more details. Coating must be allowed to cure before introducing traffic. Cure times vary based on climate conditions and range between 6–24 hours.

#### Recommended Application Coverage Rates:

# OF LAYERS	COVERAGE (approx)		THICKNESS (approx)			
	ft <sup>2</sup> /unit*	m <sup>2</sup> /unit*	WET		DRY	
			mm	mil	mm	mil
2	300	28	0.56	20	0.32	12

\*One unit is a nominal 5 gallon pail comprising Part A, Part B Hardener and Colorant (approximately 3.56 – 4.12 gallons). One unit when sprayed as a single layer covers approximately 600 ft<sup>2</sup> (55.7 m<sup>2</sup>), with an approximate thickness of 6.3 mil (0.16mm) dry.

### LIMITATIONS & PRECAUTIONS

Do not allow material to harden on any equipment. Do not apply on a flat unstamped surface. The coating will cause cracking on flat surfaces.

Product will set up quickly in hot conditions, mix only what can be used immediately. Use ice water when mixing on hot days. Ambient and surface temperatures must be 50°F (10°C) and rising before coating application. Do not ship or store unless protection from freezing is available.

### SAFETY & HANDLING

For specific information regarding safe handling of this material please refer to the Safety Data Sheet (SDS).

### CLEAN UP

Thoroughly rinse application equipment with clean water before it dries.



Represented in Canada by: HUB Surface Systems, Inc.

<https://www.hubss.com> [info@hubss.com](mailto:info@hubss.com)

See applicable warranties and guarantees for complete coverage and restrictions.

Rev 1-29-19